

TRAVERTINO • ROMANO • FINITURA

TECHNICAL DATA SHEET
tf/03

Technical qualities

TRAVERTINO ROMANO FINITURA by OIKOS is a semi-transparent paint for interiors and exteriors that has been created to protect the decoration of TRAVERTINO ROMANO. It has an extremely high yield and allows the applicator to highlight the shades and tones of the veins of natural stone. TRAVERTINO ROMANO FINITURA gives the surface water repellence and washability whilst at the same time maintaining a high level of vapour permeability protecting the surface from the weather and preventing the formation of mould and algae. The product can be coloured using the special TONER to obtain all the colours of the colour chart. It has a low odour level, is non inflammable and is friendly to both humans and the environment. Product certified in class "A+" under emissions classifications (Decree of the Official French Gazette dated 19th April 2011).



Ideal use

As finishing for TRAVERTINO ROMANO by OIKOS.

Surface preparation

Wait until TRAVERTINO ROMANO by OIKOS is completely dry.

How to apply

TRAVERTINO ROMANO naturale. To protect and maintain the natural effect of TRAVERTINO ROMANO, apply by brush, a coat of ready to use, uncoloured TRAVERTINO ROMANO FINITURA.

TRAVERTINO with a colour finish. Apply by brush a coat of undiluted and uncoloured TRAVERTINO ROMANO FINITURA, paying attention to only spread the product on the smooth parts of the surface and not inside the dimpled areas that recreate the veins of natural stone. Wait until the first coat of the finitura is dry and then proceed to apply by brush, a second coat of TRAVERTINO ROMANO FINITURA in the chosen colour, diluting the product first with 50% water. Remove excess product using a sponge so as to achieve the light dark effect caused by the different levels of absorption of the surface between the smooth areas and the dimpled ones. To obtain the desired shade of the colour chart, mix 100 ml of TONER with 1lt of TRAVERTINO ROMANO FINITURA and mix thoroughly.

Safety information

The product is free of heavy metals such as lead or chrome. It does not contain toxic solvents, aromatics or chlorides. There is no risk of any dangerous polymerisation. Normal cautionary measures for the handling of water based paints are advised.

Product

| | |
|---|--|
| Composition | Binders in water dispersion, high coverage fillers, titanium dioxide based pigments, organic and inorganic pigments, preservatives and additive to facilitate application and formation of the surface film. |
| Specific weight | 1,2kg/l ±3% |
| pH | 8.5 ÷ 10 |
| Viscosity | 3000 - 5000 CPS Brookfield (RVT 20 revs/min. a 25°C) |
| Storage temperature | +2°C ÷ +36°C. (Keep from freezing) |
| Reaction to fire | Negative if the product is applied on to a non inflammable base; water based material with a dry thickness of less than 0,600 mm |
| Water absorption W ₂₄ | TRAVERTINO CYCLE: Coefficient of water absorption at 24 hours (UNI EN 1062-3:2001) = 0.144 kg/m ² /(t*1/2) |
| Permeability to water vapour Sd | (UNI EN ISO 7783-2): high, Sd=0.008 m, μ =74.76 |
| Emission limits of Volatile Organic Compounds (VOC) according to directive 2004/42/CE | Classification: A/I; VOC: 25g/l (max); Limit Phase II (from 1.1.2010): 200 g/l |
| Emissions classification | A+under emissions classifications (Decree of the Official French Gazette dated 19th April 2011) |
| Colours | Shades of the colour chart |
| Packaging | Liters 1 – 4 |

Application

| | |
|-----------------------------|---|
| Dilution | 1st coat: ready to use, 2nd coat 50% |
| Yield | 1st coat 15 ÷ 20 m ² /l, 2nd coat 40÷ 50 m ² /l |
| Application tools | Brush, Synthetic sponge by OIKOS |
| Base coat | TRAVERTINO ROMANO by OIKOS |
| Application temperature | + 5°C ÷ +36°C (with relative humidity not exceeding 80%) |
| Drying time until touch dry | 1 ÷ 2 h (temperature = 20°C with relative humidity at 75%) |
| Drying time until Washable | 30 days (temperature = 20°C with relative humidity at 75%) |
| Drying time fully cured | 6 ÷ 8 h (temperature = 20°C with relative humidity at 75%) |
| Tools cleaning | Water |
| Warning | Protect the surface from the rain for the first 48 ÷ 72 hours after application |

No special arrangements are required for the storage, movement and transportation of the product; the containers, residue, eventual spilt material should be cleaned up using absorbent inert material such as sand, soil etc. etc. and then disposed of in accordance with the regional and national regulations in force at that time. Transportation must be carried out in accordance with international agreements.

Specifications

The surface should be thoroughly dry. Apply a first coat of ready to use FINITURA on TRAVERTINO ROMANO by OIKOS, wait four hours until dry and

then proceed to apply a second coat of FINITURA diluted 50% in the chosen colour. Remove any excess product using a sponge. All should be carried out in respect of the standard norms for application, with a cost of al m² including material and labour.

Note

The company Oikos Spa guarantees, to the best of its own technical and scientific knowledge, that the information contained in this technical data sheet is correct. Notwithstanding that indicated above, Oikos takes no responsibility for the results obtained through the use of this product in as much as it is not possible for Oikos to check or control the application method used. For this reason, we recommend that you check carefully that each product chosen, is suitable for each individual use to which it is put.

OIKOS
the ecological paint

OIKOS S.P.A. a socio unico
Via Cherubini, 2
47043 Gatteo Mare (FC)
info@oikos-group.it

ITALIA
tel. +39 0547.681412
INTERNATIONAL
tel. +39 0547.681460